We claim:

1. A process for dyeing leather with at least one dye F which has at least one alkaline-activable group of the formula A;

 $\begin{bmatrix} (X)_k \\ \\ S \\ O \end{bmatrix}$ (A)

where

denotes the bond to the dye molecule;

X is an electron-attracting radical,

k is 1, 2 or 3,

n is 0 or 1 and

B is a CH=CH₂ group or a CH₂-CH₂-Q group, where Q is an alkaline-detachable group,

15

10

5

which comprises treating the leather with an aqueous float comprising at least one dye F at a pH of not less than 7.5.

- 2. A process according to claim 1, wherein at least one radical X in the formula A is an SO₃H group.
 - 3. A process according to claim 1 or 2, wherein B in the formula A is CH=CH₂, a CH₂-CH₂-O-SO₃H^{*}group or a CH₂-CH₂-O-C(O)CH₃ group.
- 4. A process according to any preceding claim, wherein the group A is attached to the dye molecule via an -NH- or -N=N- group.
- A process according to claim 4, wherein the dye F is selected from dyes of the phthalocyanine series, anthraquinone dyes, azo dyes, formazan dyes, dioxazine dyes, actidine dyes, xanthene dyes, polymethine dyes, stilbene dyes, sulfur dyes and triarylmethane dyes.
 - 6. A process according to any preceding claim, wherein n = 0.
- 35 7. A process according to claim 6, wherein the radical A is selected from the following radicals A1 to A12:

$$HO_3S$$
 SO_2 -CH=CH₂
(A2)

$$HO_3$$
S $-- SO_2$ - CH_2 - CH_2 - O - SO_3 H (A1)

$$O_3$$
S O_2 -CH=CH O_3 S (A3)

$$HO_3S$$
 $SO_2-CH_2-CH_2-O-SO_3H$
 HO_3S
 $(A4)$

$$HO_3$$
S (A5) SO_2 -CH=CH $_2$

$$HO_3S$$
 (A6)
$$SO_2\text{-}CH_2\text{-}CH_2\text{-}O\text{-}SO_3H$$

$$+\text{IO}_3\text{S}$$
 $-\text{SO}_3\text{H}$
 $+\text{SO}_2\text{-CH=CH}_2$

$$HO_3S$$
 SO_3H (A8)
 $SO_2-CH_2-CH_2-O-SO_3H$

HO₃S SO,-CH,-CH,-O-COCH, (A9)

$$HO_3S$$
 SO_2 - CH_2 - CH_2 - O - $COCH_3$
 HO_3S
 $(A11)$

$$HO_3S$$
 $-- SO_3H$ (A12)
 $SO_2\text{-CH}_2\text{-CH}_2\text{-O-COCH}_3$

A process according to any preceding claim, wherein the dye F is selected from 8. the dyes of the general formulae I to XV:

 $Dk^{1}-N=N-[P-N=N-]_{p}Kk^{1}[-N=N-Dk^{2}]_{m}$

$$Dk^{1}-N=N-[P-N=N-]_{p}Kk^{1}[-N=N-Dk^{2}]_{m}$$
 (I)

$$Dk^{1}-N=N-Napht^{1}[-N=N-Tk^{1}]_{r}[-N=N-Kk^{1}]_{k}[-N=N-Dk^{2}]_{n}$$
 (II)

10

5

	Dk¹-N=N-Na	pht ¹ -N=N-Tk ¹ -N=N-Kk ¹ -N=N-Tk ² -N=N-Napht ² -N=N-Dk ²	(III)
5	Dk¹-N=N-Kk¹-N=N-Tk¹-N=N-Kk²-N=N-Dk²		
	Dk ¹ -N=N-[P-N=N-] _p Napht ¹ [-N=N-R] _r -NH-Tr ¹ -NH-Dk ²		(V)
	Dk¹-N=N-P-NH-Tr¹-NH-R-N=N-Dk²		(VI)
10	Dk¹-N=N-Nap	oht ¹ -N=N-Tk ¹ -N=N-P-NH-Tr ¹ -NH-Dk ²	(VII)
	Dk ¹ -N=N-Napht ¹ -NH-Tr ¹ -NH-P-NH-Tr ² -NH-Napht ² -N=N-Dk ² (VIII		
15	Dk1-N=N-Napht1-NH-Tr1-NH-Tk1-NH-Tr2-NH-Napht2-N=N-Dk2		(IX)
	Dk¹[-N=N-L] _k ·	-NH-Tr¹-NH-M-N=N-Napht¹-N=N-P-NH-Tr²-NH-[R-N=N-] _n Dk²	(X)
	Dk¹-N=N-Kk¹-N=N-Tk¹-NH-Tr¹-NH-Dk²		(XI)
20	Dk¹-N=N-[P-N	$I=N-]_pR-N=N-Kk^1[-N=N-Dk^2]_n$	(XII)
	Dk¹-N=N-Pyr-A		(XIII)
25	Kk ³ -N=N-Tk ¹ -N=N-Kk ¹ -N=N-A		(XIV)
	$Dk^{1}-N=N-P-N=N-Kk^{1}-N=N-R-N=N-Dk^{2}$		(XV)
	where		
30	k, n, p and r	are independently 0 or 1 subject to the condition that k+n+r formula II is = 1, 2 or 3;	in the
	m	is 0, 1 or 2;	
35	Dk ¹ , Dk ²	independently represent a radical derived from an aromatic amine or denotes a group of the formula A subject to the condition that in each of the formulae I - XII and XV at least one of Dk ¹ and Dk ² represents a radical of the formula A	
40	Kk ¹ , Kk ² independently represent a mono-, di- or trivalent aromatic radical which derives from benzene, naphthalene, pyrazole, quinoline,		

diphenylamine, diphenylmethane, pyrimidine, pyridine or diphenyl ether and which may optionally comprise one or more of the following radicals as substituents: SO₃H, COOH, CN, CONH₂, OH, NH₂, NO₂, halogen, C₁-C₄-alkyl, C₁-C₄-hydroxyalkyl, carboxy-5 C₁-C₄-alkyl, C₁-C₄-alkoxy, C₁-C₄-alkylamino, C₁-C₄-dialkylamino. C₁-C₄-alkylaminocarbonyl, C₁-C₄-dialkylaminocarbonyl, C₁-C₄alkylcarbonylamino, N-(C₁-C₄-alkylcarbonyl)-N-(C₁-C₄alkylcarbonyl)amino, C₁-C₄-alkylaminocarbonyloxy, C₁-C₄dialkylaminocarbonyloxy, C₁-C₄-alkylaminocarbonylamino, C₁-C₄-10 dialkylaminocarbonylamino, phenylaminocarbonyloxy. phenylaminocarbonylamino, C₁-C₄-alkoxycarbonylamino, C₁-C₄hydroxy-C₁-C₄-alkylamino, carboxy-C₁-C₄-alkylamino, phenylcarbonylamino, C₁-C₄-alkylsulfonyl, hydroxy-C₁-C₄alkylsulfonyl, C₁-C₄-alkylaminosulfonyl, C₁-C₄-alkylsulfonylamino. 15 phenylsulfonyl, phenylsulfonylamino, formamide, a radical of the formula SO₂NR⁵⁶R⁵⁷, where R⁵⁶ and R⁵⁷ independently represent hydrogen, C₁-C₄-alkyl, formyl, C₁-C₄-alkylcarbonyl, C₁-C₄alkyloxycarbonyl, NH₂-CO or C₁-C₄-alkylaminocarbonyl, C₁-C₄alkylaminosulfonylamino, di-C₁-C₄-alkylaminosulfonylamino, 20 phenylsulfonylamino which may be substituted on the phenyl ring by one or two substituents selected from C₁-C₄-alkyl, C₁-C₄alkoxy or halogen, or 5- or 6-membered heterocyclyl, which is optionally substituted by 1, 2 or 3 of the following radicals: OH, halogen, C₁-C₄-alkyl or phenyl, 5-membered aromatic 25 heterocyclyl optionally bearing on the nitrogen a phenyl or naphthyl group which can optionally comprise one or two of the following radicals: OH, SO₃H, C₁-C₄-alkyl, and/or C₁-C₄-alkoxy; Kk³ is a monovalent radical which derives from benzene, pyrimidine, 30 pyridine or naphthalene and which optionally comprises 1 or 2 hydroxysulfonyl groups and optionally 1, 2 or 3 further substituents selected from SO₃H, COOH, CN, CONH₂, OH, NH₂, NO₂, halogen, C₁-C₄-alkyl, C₁-C₄-hydroxyalkyl, carboxy-C₁-C₄alkyl, C₁-C₄-alkoxy, C₁-C₄-alkylamino, C₁-C₄-dialkylamino, 35 C₁-C₄-alkylaminocarbonyl, C₁-C₄-dialkylaminocarbonyl, C₁-C₄-alkylcarbonylamino, N-(C₁-C₄-alkylcarbonyl)-N-(C₁-C₄alkylcarbonyl)amino, C₁-C₄-alkylaminocarbonyloxy, C₁-C₄dialkylaminocarbonyloxy, C₁-C₄-alkylaminocarbonylamino, C₁-C₄dialkylaminocarbonylamino, phenylaminocarbonyloxy. 40 phenylaminocarbonylamino, C₁-C₄-alkoxycarbonylamino, C₁-C₄-

hydroxy-C₁-C₄-alkylamino, carboxy-C₁-C₄-alkylamino,

phenylcarbonylamino, C₁-C₄-alkylsulfonyl, hydroxy-C₁-C₄alkylsulfonyl, C₁-C₄-alkylaminosulfonyl, C₁-C₄-alkylsulfonylamino, phenylsulfonyl, phenylsulfonylamino, formamide, a radical of the formula SO₂NR⁵⁶R⁵⁷, where R⁵⁶ and R⁵⁷ independently represent 5 hydrogen, C₁-C₄-alkyl, formyl, C₁-C₄-alkylcarbonyl, C₁-C₄alkoxycarbonyl, NH₂-CO or C₁-C₄-alkylaminocarbonyl, C₁-C₄alkylaminosulfonylamino, di-C₁-C₄-alkylaminosulfonylamino, phenylsulfonylamino which may be substituted on the phenyl ring by one or two substituents selected from C₁-C₄-alkyl, C₁-C₄-10 alkoxy or halogen, or 5- or 6-membered heterocyclyl, which is optionally substituted by 1, 2 or 3 of the following radicals: OH, halogen, C₁-C₄-alkyl or phenyl, 5-membered aromatic heterocyclyl optionally bearing on the nitrogen a phenyl or naphthyl group which can optionally comprise one or two of the 15 following radicals: OH, SO₃H, C₁-C₄-alkyl, and/or C₁-C₄-alkoxy; Tk¹, Tk² independently represent a divalent aromatic radical which derives from benzene, diphenylamine, biphenyl, diphenylmethane, 2-phenylbenzimidazole, phenylsulfonylbenzene, 20 phenylaminosulfonylbenzene, stilbene or phenylaminocarbonylbenzene which may each optionally comprise one or more of the following radicals as substituents: SO₃H, COOH, OH, NH₂, NO₂, halogen, C₁-C₄-alkyl; 25 L, M, P and R independently represent a divalent aromatic radical which derives from benzene or naphthalene which may each optionally comprise one or more, for example 1, 2, 3, 4 or 5, of the following radicals as substituents: SO₃H, COOH, CN, CONH₂, OH, NH₂, NO₂, halogen, C₁-C₄-alkyl, C₁-C₄-hydroxyalkyl, carboxy-C₁-C₄-30 alkyl, C₁-C₄-alkoxy, C₁-C₄-alkylamino, C₁-C₄-dialkylamino, C₁-C₄-alkylaminocarbonyl, C₁-C₄-dialkylaminocarbonyl, C₁-C₄-alkylcarbonylamino, N-(C₁-C₄-alkylcarbonyl)-N-(C₁-C₄alkylcarbonyl)amino, C₁-C₄-alkylaminocarbonyloxy, C₁-C₄dialkylaminocarbonyloxy, C₁-C₄-alkylaminocarbonylamino, C₁-C₄-35 dialkylaminocarbonylamino, phenylaminocarbonyloxy, phenylaminocarbonylamino, C₁-C₄-alkoxycarbonylamino, C₁-C₄hydroxy-C₁-C₄-alkylamino, carboxy-C₁-C₄-alkylamino. phenylcarbonylamino, C₁-C₄-alkylsulfonyl, hydroxy-C₁-C₄alkylsulfonyl, C₁-C₄-alkylaminosulfonyl, C₁-C₄-alkylsulfonylamino, 40 phenylsulfonyl, phenylsulfonylamino, formamide, a radical of the formula SO₂NR⁵⁶R⁵⁷, where R⁵⁶ and R⁵⁷ independently represent

11.

hydrogen, C₁-C₄-alkyl, formyl, C₁-C₄-alkylcarbonyl, C₁-C₄alkoxycarbonyl, NH₂-CO or C₁-C₄-alkylaminocarbonyl, C₁-C₄alkylaminosulfonylamino, di-C1-C4-alkylaminosulfonylamino, phenylsulfonylamino which may be substituted on the phenyl ring 5 by one or two substituents selected from C₁-C₄-alkyl, C₁-C₄alkoxy or halogen, or 5- or 6-membered heterocyclyl, which is optionally substituted by 1, 2 or 3 of the following radicals: OH, halogen, C₁-C₄-alkyl or phenyl, 5-membered aromatic heterocyclyl optionally bearing on the nitrogen a phenyl or 10 naphthyl group which can optionally comprise one or two of the following radicals: OH, SO₃H, C₁-C₄-alkyl, and/or C₁-C₄-alkoxy; Napht¹, Napht² independently represent a divalent radical which derives from naphthalene and which comprises 1 or 2 hydroxysulfonyl groups 15 and may optionally comprise 1, 2 or 3 further substituents selected from OH, NH₂, C₁-C₄-alkylamino, C₁-C₄-dialkylamino, C₁-C₄-alkylsulfonylamino, phenylsulfonylamino, 4-methylphenylsulfonylamino, C₁-C₄-alkylaminosulfonyl, di-C₁-C₄alkylaminosulfonyl, phenylaminosulfonyl, 20 4-methylphenylaminosulfonyl and NHC(O)Rx radicals, where Rx hydrogen, C₁-C₄-alkyl, maleyl or phenyl: Pyr represents pyrazole-1,4-diyl which attaches through the nitrogen atom to the A group and optionally comprises one or 25 2 substituents selected from halogen, C₁-C₄-alkyl, hydroxyl or C₁-C₄-alkoxy; Tr¹, Tr² independently represent a 1,3,5-triazine-2,4-diyl radical which optionally further comprises a halogen atom, a methyl group or a 30 methoxy group as substituent, and the metal complexes of these dyes. 9. A process according to any preceding claim, wherein initially the leather is 35 treated with the aqueous float comprising at least one dye F at a pH in the range from 3 to 6.5 and then a pH of at least 7.5 is set in the float. 10. A process according to any one of claims 1 to 7, wherein the dyeing is carried out as a one-stage process. 40

A process according to any preceding claim, wherein the dyeing is carried out

5

15

35

40

before retanning.

- 12. A process according to any preceding claim, wherein the dyeing is effected at temperatures in the range from 10 to 60°C.
- 13. The use of dyes F which comprise at least one alkali-activable group of the formula A as defined in claim 1 and mixtures thereof for dyeing leather at pH ≥ 7.5.
- 10 14. Dyes F of the general formulae IIa, IIIa or IVa

$$Dk^{1}-N=N-Napht^{1}-N=N-Tk^{1}-[N=N-Kk^{1}]_{k}-N=N-]_{k}Dk^{2}$$
 (IIa)

- $Dk^{1}-N=N-Napht^{1}-N=N-Tk^{1}-N=N-Kk^{1}-N=N-Tk^{2}-N=N-Napht^{2}-N=N-Dk^{2}$ (IIIa)
- $Dk^{1}-N=N-Napht^{1}-N=N-Tk^{1}-N=N-Napht^{2}-N=N-Dk^{2}$ (IVa)
- where Dk¹, Dk², Napht¹, Napht² and Kk¹ are each as defined above, k is 0 or 1 and where Tk¹ and Tk² independently represent a divalent radical which derives from biphenyl, diphenylmethane, 2-phenylbenzimidazole, phenylsulfonylbenzene, phenylaminosulfonylbenzene, diphenylamine, stilbene or phenylaminocarbonylbenzene and may optionally comprise one or more of the following radicals as substituents: SO₃H, COOH, OH, NH₂, NO₂, halogen, C¹-C⁴-alkyl, although Tk¹ in formula Ila does not represent a diphenylaminederived radical when k is = 0 and either or both of the radicals Dk¹ and Dk² represent a radical of the formula A as defined in claim 1.
 - 15. Dyes F of the general formula IIb

30
$$A-N=N-Napht^1-N=N-Tk^1-N=N-Kk^1-[N=N-Dk^2]_n$$
 (IIb)

where A, Dk², Napht¹ and Kk¹ are each as defined above, n is 0 or 1 and where Tk¹ represents a divalent radical which derives from biphenyl, diphenylmethane, 2-phenylbenzimidazole, phenylsulfonylbenzene, phenylaminosulfonylbenzene, diphenylamine, stilbene or phenylaminocarbonylbenzene and may optionally comprise one or more of the following radicals as substituents: SO₃H, COOH, OH, NH₂, NO₂, halogen, C₁-C₄-alkyl, where Tk¹ does not represent a diphenylamine-derived radical when n is = 0 and where Dk² radical may also represent a radical of the formula A as defined in claim 1.

16. Dyes according to claim 14 or 15, wherein Tk¹ and/or Tk² in the formulae IIa, IIb,

Illa or IVa represents a radical of the general formula

5 where *** represent the bonds to the azo groups.

17. Dyes according to any one of claims 14 to 16, wherein Napht¹ and/or Napht² represent a bivalent radical of the general formula

$$\begin{array}{ccc}
R^1 & R^2 \\
& & \\
(SO_3^-)_s & (SO_3^-)_t
\end{array}$$
(II)

10

15

where R^1 and R^2 are independently hydrogen, OH, NH₂ or NHC(O)R³, where R³ represents hydrogen, C₁-C₄-alkyl, maleyl or phenyl and at least one of R¹ and R² is other than hydrogen, \cdots represent the bonds to the azo groups, s and t represent 0 or 1 and the s + t sum is 1 or 2.

- 18. Dyes according to any one of claims 14 to 17, wherein either or both of the radicals Dk¹ and Dk² represent one of the A1 to A12 radicals defined in claim 7.
- 20 19. Dyed leather obtainable by a dyeing process according to any one of claims to 1 to 12.
 - 20. Leather according to Claim 19 for handwear, footwear, automobiles, apparel or furniture.